



DeSoto® 515X346 Epoxy Polyamide Corrosion Preventative Bonding Primer

TECHNICAL DATA SHEET

Product Description

DeSoto® 515X346 is a flexible, high tensile strength epoxy bonding primer designed for use with paste or high tack, room temperature curing adhesives. It offers protection of the adhesive bond from corrosion while maintaining adequate shear and peel strength.

- Excellent adhesion and corrosion resistance
- Excellent fluid resistance
- Compatible with all non-electrostatic spray equipment
- Can be applied in a wide range of conditions
- Compatible with room temperature adhesives
- Service temperature -54 °C to 177 °C (-65 °F to 350 °F)

Components



Mix ratio (by volume):

- | | |
|---------------------------------|---------|
| • 515X346 (base component) | 4 parts |
| • 910X520 (activator component) | 1 part |
| • 020-702 (thinner component) | 4 parts |

Specifications

515X346 primer is qualified to:

- | | |
|----------------|---------------|
| • MAP-CC 10185 | • STMK 1144 |
| • MSFC-3615 | • STMK 719-2 |
| • PWA-SP 1138 | • STMO 876-01 |

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

515X346 primer is listed on:

- | | |
|---------------------|------------|
| • BAC 5010 Type 102 | • DPM 8951 |
| • BAC 5710 Type 60 | |

Note: PPG Aerospace recommends you check the most recent Process Standard for updated information.

Product Compatibility:

515X346 primer is compatible with the following topcoat specifications:

- | | |
|------------------------------|-----------------------|
| • BMS 10-60 Type I & Type II | • BMS 10-72 Type VIII |
|------------------------------|-----------------------|



DeSoto® 515X346 Epoxy Polyamide Corrosion Preventative Bonding Primer

Surface Preparation and Pretreatments



DeSoto® 515X346 epoxy polyamide bonding primer can be applied over clean, properly prepared aluminum and composite surfaces. Aluminum surfaces shall be treated with materials conforming to MIL-C-5541 or equivalent.

Instructions for Use

Mixing Instructions:

Prior to mixing, thoroughly shake the base component. Add the activator to the base component and stir well, and then add thinner under agitation. Maintain constant agitation for 10 minutes to ensure proper mixing. Induction time is required.

Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13 ° and 35 °C (55 ° to 95 °F). The minimum temperature of the paint components should be 13 °C (55 °F) prior to mixing.



Induction Time:


Temperature	13 - 21 °C (55 - 70 °F)	22 - 28 °C (71 - 84 °F)	>29 °C (>85 °F)
Induction Time Required	1 ½ hour	1 hour	30 minutes



Viscosity: (23 °C/73 °F)

- | | |
|-------------------------|------------------|
| • #2 Signature Zahn cup | 16 to 20 seconds |
| • #4 Ford cup | 10 to 15 seconds |
| • ISO 4mm cup | 18 to 22 seconds |
| • BSB3 cup | 26 to 30 seconds |
| • BSB4 cup | 15 to 17 seconds |
| • AFNOR #2.5 cup | 45 to 56 seconds |
| • AFNOR #4 cup | 15 to 17 seconds |

Note: Viscosities quoted are the typical ranges obtained when using specified mix ratio.



Pot Life:

8 hours @ 21 - 25 °C (70 - 77 °F)



DeSoto® 515X346 Epoxy Polyamide Corrosion Preventative Bonding Primer

Application Guidelines

Recommended Application Conditions:

Temperature 15 - 30 °C (59 - 86 °F)
Relative Humidity 20 - 90%

Application:


Ground the aircraft and the application equipment before priming. Stir the primer slowly during the application. The suggested film thickness is 20 to 30 microns (0.8 to 1.2 mils). This can be accomplished with one medium coat with a 50% overlap.

These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.



Theoretical Coverage:

9.1 square meters/liter at 25 microns dry film (375 square feet/gallon at 1 mil dry film)
Recommended dry film thickness; 20 to 30 microns (0.8 to 1.2 mils)



Dry Film Density:

1.6 grams/cubic centimeter (13.33 pounds/gallon)

Dry Film Weight:

40.0 grams/square meter at 25 microns dry film (0.00817 pounds/square feet at 1 mil dry film)



Equipment:

515X346 is compatible with all non-electrostatic spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

Equipment Cleaning:

Clean spray equipment as soon as possible after use. Flush spray equipment with DeSoto® CN20, DeSoto® CN44, or Desoclean™ 45 high performance solvent cleaner.



DeSoto[®] 515X346 Epoxy Polyamide Corrosion Preventative Bonding Primer

Physical Properties (product)



Color: Green



Gloss: Not Applicable



Dry Times	13 - 21 °C (55 - 70 °F)	22 - 28 °C (71 - 84 °F)	>29 °C (>85 °F)
Tack Free	3 hours	2 hours	1 ½ hours
Dry Hard	18 hours	16 hours	14 hours
Full Cure	7 days	7 days	7 days

Accelerated cure:

For Dry Hard

Allow 1 hour flash off at 24 °C ± 3 °C (75 °F ± 10 °F)
followed by 30 minutes at 49 °C (140-160 °F)

For Full Cure

Allow 1 hour flash off at 24 °C ± 3 °C (75 °F ± 10 °F)
followed by 16 - 24 hours at 49 °C (140-160 °F)



VOC (EPA method 24):

Mixed, ready to use VOC	650 grams/liter
Base Component	507 grams/liter
Activator Component	532 grams/liter
Thinner Component	832 grams/liter



Flash point closed cup:

Base Component	23 °C (74 °F)
Activator Component	7 °C (45 °F)
Thinner Component	-1 °C (32 °F)



DeSoto[®] 515X346 Epoxy Polyamide Corrosion Preventative Bonding Primer

Shelf Life:

12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

Note: The coating shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5 °C to 35 °C (41 °F to 95 °F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.



DeSoto[®] 515X346 Epoxy Polyamide Corrosion Preventative Bonding Primer

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.

12780 San Fernando Road
Sylmar, CA 91342

www.ppgaerospace.com

Issue Date: 7/14
Lit: 4008