

DeSoto® 515X349 Exterior Primer

TECHNICAL DATA SHEET

Product Description

DeSoto® 515X349 exterior primer is a conventional solids urethane compatible epoxy coating. This primer was formulated to protect aluminum and composite substrates from corrosion.

- Compatible with Desothane® HS topcoats
- Excellent adhesion to aluminum and composite surfaces
- Can be applied with all current non-electrostatic spray equipment
- Improved Skydrol® resistance
- Can be applied in a wide range of conditions
- Difficult to remove with chemical strippers
- Service temperature -54°C to 177°C (-65°F to 350°F)

Components



Mix ratio (by volume):

- | | |
|---------------------------------|--------|
| • 515X349 (base component) | 1 part |
| • 910X533 (activator component) | 1 part |

Specifications



515X349 primer is qualified to:

- | | |
|---------------------------------------|----------------------|
| • BMS 10-79 Type III Class A Grade A | • SMS 111204 Type I |
| • DHMS C4.04 Type 6 Class B Grade A | • STM0791 |
| • DHMS C4.18 Type III Class A Grade A | • STMGK 189 |
| • DMS 2144 Composition A | • STM-P-K104 |
| • MS37.14.03 | • VMS C4.18 Type III |

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

DeSoto[®] 515X349 Exterior Primer

Product Compatibility:

515X349 primer is compatible with the following topcoat specifications:

- AMS 3095
- BAC 5312
- BAMS 565-002 Class A Grade B
- BAMS 565-009 Type II Class Grade B
- BMS 10-60 Type II Class B Grade D
- BMS 10-72 Type VIII
- BMS 10-125 Type III Grade D
- BMS 10-126 Type I Grade D
- CMFS037
- CMS-CT-101 Type I
- D6-1816
- DHMS C4.04 Type VI Class B Grade B
- DMS 2143 Type 1 Class 1 Composition C
- DPM 6456
- DPM 6546
- FEDEX STANDARD
- GAMPS 3209
- GP110AEE
- MEP 10-069
- MM1276 Type II
- MS100029E Class HS
- RMS 430 Type II
- SMS-111207 Type 1
- VMS C4.04 Type VI Class B Grade B

Surface Preparation and Pretreatments



515X349 primer can be applied over, MIL-C-5541, or chromic acid anodized aluminum.

Instructions for Use



Mixing Instructions:

Prior to mixing, thoroughly shake the base component. Add activator to base component and stir well. Maintain constant agitation for 10 minutes to ensure proper mixing. Induction time is required based on temperature.

Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.



Induction Time:

Temperature	13 - 21°C (55 - 70°F)	22 - 28°C (71 - 84°F)	>29°C (>85°F)
Induction Time Required	30 minutes	30 minutes	30 minutes


DeSoto[®] 515X349 Exterior Primer



Viscosity: (23°C/73°F)

• #1 Signature Zahn cup	30 to 40 seconds
• #2 Signature Zahn cup	16 to 20 seconds
• #4 Ford cup	12 to 15 seconds
• ISO 3mm cup	37 to 50 seconds
• ISO 4mm cup	18 to 22 seconds
• BSB3 cup	26 to 30 seconds
• BSB4 cup	15 to 17 seconds
• AFNOR #2.5 cup	45 to 56 seconds
• AFNOR #4 cup	14 to 16 seconds

Note: Viscosities quoted are the typical ranges obtained when using specified mix ratio.



Pot Life:

8 hours @ 21 - 25°C (70 - 77°F)

Application Guidelines

Recommended Application conditions:

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%

Application:


Ground the aircraft and the application equipment before priming. Stir the primer slowly during the application. The suggested film thickness is 12.5 to 22.5 microns (0.5 to 0.9 mils). This can be accomplished with one medium coat with a 50% overlap

These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.



Theoretical Coverage:

9.5 square meters/liter at 25 microns dry film (375 square feet/gallon at 1 mil dry film)
Recommended dry film thickness; 12.5 to 22.5 microns (0.5 to 0.9 mils)



Dry Film Density:

1.8 grams/cubic centimeter (15.0 pounds/gallon)

Dry Film Weight:

45.0 grams/square meter at 25 microns dry film (0.0095 pounds/square feet at 1 mil dry film)

DeSoto[®] 515X349 Exterior Primer



Equipment:

515X349 primer is compatible with all current non-electrostatic spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

Equipment Cleaning:

Clean spray equipment as soon as possible after use. Flush spray equipment with DeSoto[®] CN20, DeSoto[®] CN44, or Desoclean™ 45 high performance solvent cleaner.

Physical Properties (product)



Color: Dark Green



Gloss: Not Applicable



Dry Times	13 - 21°C (55 - 70°F)	22 - 28°C (71 - 84°F)	>29°C (>85°F)
Tack Free	45 minutes	30 minutes	20 minutes
Dry to Tape	3 hours	2 hours	1 ½ hours
Dry to Topcoat	3 - 72 hours	2 - 72 hours	1 ½ - 72 hours
Dry to Fly	72 hours	48 hours	36 hours
Full Cure	7 days	7 days	7 days

Accelerated cure:

Allow 15 minutes flash off at 24°C ± 3°C (75°F ± 10°F) followed by 30 minutes at 60°C (140°F)



DeSoto[®] 515X349 Exterior Primer



VOC:

Mixed, ready for use VOC (EPA method 24)	650 grams/liter
Base Component	514 grams/liter
Activator Component	804 grams/liter



Flash point closed cup:

Base Component	-1°C (31°F)
Activator Component	7°C (45°F)

Shelf Life:

12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

Note: Shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.



DeSoto® 515X349 Exterior Primer

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Desoclean, Desothane, DeSoto, and Skydrol are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.

12780 San Fernando Road
Sylmar, CA 91342

www.ppgaerospace.com

Issue Date: 8/15
Lit: 4185